

# bonshure®

# e-3

## waterborne acrylic finish

acrylic top & primer

e  
a  
s  
y  
f  
i  
n  
i  
s  
h

### Product Introduction

bonshure top & primer e-3 is an economical product suitable for timber flooring & wood floor.

### Features

- \*without the stink
- \*easy to apply and clear
- \*high resistance wear.
- \*no bubbling , beautiful leveling.
- \*Fast drying
- \*excellent durability
- \* non yellowing

### Preparation

When you using the bonshure acrylic top & primer you must measured floor surface must be cleaned, dry with dust, dirt, wax and grease removed. Before using you must measure wood floors not be apply any other primer . Do not thin the product. Shake well before use.

### Application

After apply bonshure acrylic top & primer 1-2 coat over the surface. 2-3 hours dry time for one coat. we approximately after 6 hours final coat can step on the floor. After four night final coat the floor can be mop with dry cloth on the floor. Coating system reaches final hardness after approx, 1 day

### Technical Data

Solid content	33%
Application Tools	sponge , floor coater, 10 inch formica, roller
Intercoat abrasion	can be recoated without in tercoat abrasion within 24 hours.
Suitable use	kitchens, living rooms, active homes with children, office, hospital, shop,etc
Dry Time	2-3 hours for one coat(if to encounter air temperature is below 28°C dry time is not stable)
Sand paper	water sand paper grit 240-320
shelf Life	Shelf life 12 months in opened container.
Gloss level	gloss 20, matt 80%.
Coverage	1500-1600 square feet / 10 kg
Storage	Store away from direct sunlight .
Package size	10 kg
Technology	German
Material	German

acrylic top coat



Our information based on laboratory tests and practical experience and may as such be considered a guide in connection with choice of product and working method. As the users working conditions is beyond our control, we do not assume any responsibility for the result. Our responsibility covers exclusively personal injury or damage to property which actually have been proved subsequent to faults and defects in one of the products manufactured by us.

KSC INDUSTRIES (M) SDN BHD No16, Jalan Sungai Jeluh 32/189, Bukit Naga Seksyen 32 ,40460 Shah Alam selangor.

Tel:(03)-51668790 Fax: (03)-51670942 Website:www.ksc-monatec.com Email: info@ksc-monatec.com.